

What is claimed is:

1. A packaged produce product comprising a package formed from at least one coextruded polyamide film comprising at least one first layer formed from a polyamide
5 selected from the group consisting of nylon 6, nylon 66 and blends thereof, and at least one second layer of nylon 6,66 in contact with said first layer, and produce contained within said package, said package being formed from at least one polyamide film being heat sealed via said nylon 6,66 layer.
- 10 2. The product of claim 1, wherein said first layer comprises nylon 6.
3. The product of claim 2, wherein said nylon 6 moiety is present in said nylon 6,66 layer in an amount from about 10 to about 95 weight percent.
- 15 4. The product of claim 2, wherein said nylon 6 moiety is present in said nylon 6,66 layer in an amount from about 55 to about 95 weight percent.
5. The product of claim 2, wherein said nylon 6 moiety is present in said nylon 6,66 layer in an amount from about 70 to about 90 weight percent.
- 20 6. The product of claim 2, wherein the thickness of said polyamide film ranges from about 1 to about 50 μm .
7. The product of claim 2, wherein the thickness of said polyamide film ranges from
25 about 5 to about 40 μm .
8. The product of claim 2, wherein the thickness of said polyamide film ranges from about 10 to about 30 μm .
- 30 9. The product of claim 2, wherein said polyamide film is perforated.

10. The product of claim 2, wherein the heat seal strength of said polyamide film is at least about 700 grams.

11. The product of claim 1, wherein said package is formed from a single polyamide film which is heat sealed to itself via said nylon 6,66 layer.

12. The product of claim 1, wherein said package is formed from two polyamide films which are overlapped, with said nylon 6,66 layer of both polyamide films being heat sealed together.

10

13. A packaged produce product comprising a package formed from at least one coextruded polyamide film comprising at least one layer of nylon 6, and at least one layer of nylon 6,66 in contact with said nylon 6 layer, and produce contained within said package, said package being formed from at least one polyamide film being heat sealed via said nylon 6,66 layer.

15

14. The product of claim 13, wherein said nylon 6 moiety is present in said nylon 6,66 layer in an amount from about 55 to about 95 weight percent.

15. The product of claim 13, wherein said nylon 6 moiety is present in said nylon 6,66 layer in an amount from about 70 to about 90 weight percent.

20

16. The product of claim 13, wherein the thickness of said polyamide film ranges from about 1 to about 50 μm .

25

17. The product of claim 13, wherein the thickness of said polyamide film ranges from about 10 to about 30 μm .

18. The product of claim 13, wherein said polyamide film is perforated.

30

19. The product of claim 13, wherein the heat seal strength of said polyamide film is at least about 700 grams.

20. The product of claim 13, wherein said package is formed from a single polyamide
5 film which is heat sealed to itself via said nylon 6,66 layer.

22. The product of claim 13, wherein said package is formed from two polyamide films which are overlapped, with said nylon 6,66 layer of both polyamide films being heat sealed together.

10

23. The product of claim 13, wherein said package comprises a bag.

24. The product of claim 13, wherein said package comprises a pouch.